



ELRASA - ASeXW™ (Aluminium Sulphate)

Technical Datasheet

1. Technical Datasheet

Property	Specification
Physical Properties	
Appearance	White crystalline solid.
Physical Form	White crystalline solid
Odor	Odorless
Molecular Weight	342.15 g/mol
Density	2.71 g/cm ³
Specific Gravity	2.71 (water = 1)
Refractive Index	1.47
pH (aqueous solution)	≥ 2.9 (5% solution)
Assay / Purity	Water-soluble aluminium of not less than 9.0% w/w as Al or 17.0% w/w as Al ₂ O ₃
Chemical Properties	
Ionic Nature	Ionic salt. Dissociates in water to form aluminum ions (Al ³⁺) and sulfate ions (SO ₄ ²⁻).
Incompatibilities	Water/moisture, strong bases (e.g., sodium hydroxide), strong oxidizing agents, ammonia, amines, and many metals in the presence of water.
Hazardous Reactions / Decomposition Products	Decomposes on heating (above 770 °C) to produce toxic and corrosive fumes of sulfur oxides (sulfur trioxide, sulfur dioxide) and aluminum oxide. Reacts with water to form a dilute sulfuric acid solution.
Thermal Properties	
Melting Point	770 °C (decomposes)
Boiling Point	Decomposes
Flash Point	Non-combustible / Non-flammable
Decomposition Temperature	Begins to lose crystal water at 250 °C; decomposes to γ-alumina and sulfur trioxide between 580 and 900 °C.
Thermal Stability	Stable under normal temperatures and pressures. Hygroscopic; absorbs moisture from the air.
Solubility	
Solubility in Water	36.4 g/100 mL at 20°C; 89 g/100 mL at 100°C.



Property	Specification
Solubility in Ethanol	Insoluble or slightly soluble.
Solubility in Benzene	Practically insoluble.

2. Dosing by Application

Application	Recommended / Max Dosage
Drinking Water Treatment (Coagulation)	5 to 200 mg/L. May be as high as 500 mg/L for highly turbid water.
Wastewater Treatment (Coagulation)	10 - 60 ppm (mg/L).
Wastewater Phosphorus Removal	10 - 30 mg/L.
General Impurity Limits (Maximum Dosage Basis)	Maximum dosage of 100 mg/L is used as a basis for calculating impurity limits in drinking water.

The information and data contained herein are believed to be accurate but may not be all inclusive and should only be used as a guide. The information is furnished upon the condition that the person receiving it shall make his own determination of the suitability of the product for his particular use and on condition that they assume the risk of the use thereof.

EXPLORE ELCHEMY'S PRODUCT PORTFOLIO

[ELRASA - ASeXW™ \(Aluminium Sulphate\)](#) | [Browse Catalog](#) | [Connect with us](#)